

PMR FINISHES

Proven mildew resistant finishes for demanding building environments



PRODUCT DESCRIPTION

Dryvit Proven Mildew Resistant (PMR) finishes are designed to inhibit the growth of mildew in difficult mould and mildew-prone environments. These 100% acrylic finishes incorporate state of the art chemistry developed to keep buildings mildew free longer. PMR finishes are offered in seven textures: Quarzputz, Limestone, Sandblast, Sandpebble Fine, Sandpebble, Sandpebble 2 and Freestyle. It is the finishing touch that adds lasting colour and texture to exterior walls. Dryvit finishes will remain cleaner longer with reduced dirt pickup and improved mildew resistance.

FEATURES & BENEFITS

| FEATURE | BENEFIT |
|----------------------------|----------------------------------|
| • Acrylic based finishes | Good dirt repellence |
| • Proven Mildew Resistance | Reduced mould growth |
| • Extensive colour range | Decorative and visually pleasing |
| • Vapour permeable | Allows vapour transmission |

PROPERTIES

Drying time - drying of the finishes is dependent on the air temperature, relative humidity and coating thickness. Under average drying conditions 20°C, 55% RH, protect work from rain for at least 24 hours. Lower temperatures and higher humidities will require that the PMR finish be protected for longer during the drying period.

Temporary protection - during and after work, until the PMR finishes are completely dry, finish must be protected against adverse weather conditions (strong wind, rain, high temperature, sunshine, fog, etc.).

DS.EN.04.52.08



USES

PMR finishes can be applied over properly prepared substrates such as Dryvit External Wall Insulation (EWI) and Anti Crack Render (ACR) systems, exterior masonry, render, precast and cast-in-situ concrete and other approved substrates.

COLOURS

All finishes are available in standard colours as well as custom colours.

TEXTURE

The finishes achieve a texture, which is governed by aggregate size as well as the trowel motion in finishing the wall. Quarzputz produces the coarsest textured finish of the range, which is ideal for masking surface imperfections. Limestone replicates the appearance of limestone blocks. Sandblast produces a sand-like texture, Sandpebble a medium pebbly texture, Sandpebble Fine a fine pebble finish and Freestyle allows an ornamental trowel texture to be achieved.

PACKAGING

The finishes are shipped in 24.72 kg pails.

COVERAGE

Quarzputz: approximately 9 m² per pail
Sandpebble Fine: approximately 12 m² per pail.
Sandpebble: approximately 9 m² per pail.
Sandpebble 2: approximately 7 m² per pail.
Sandblast: approximately 10 m² per pail
Limestone: approximately 11 m² per pail (when applied in 2 coats)
Freestyle: approximately 12-21m² per pail (dependent on thickness).

All coverages are approximate and depend upon substrate profile, details and individual application technique. Estimates take no account of wastage.



PMR FINISHES

DS.EN.04.52.08

Proven Mildew Resistant finishes for demanding building environments

TEXTURE AGGREGATE SIZES

| PMR Texture | Nominal Aggregate Size (mm) |
|-----------------|-----------------------------|
| Quarzputz | 2.0 |
| Limestone | 0.6 |
| Sandblast | 1.2 |
| Sandpebble Fine | 1.2 |
| Sandpebble | 1.6 |
| Sandpebble 2 | 2.0 |
| Freestyle | 0.6 |

PREPARATION

Surfaces must be smooth, clean, dry, structurally sound and free of efflorescence, grease, loose paint, oil, form release agents and curing compounds. Air and surface temperature for application of PMR finishes must be from 4°C to 25°C and must remain so for a minimum of 24 hours. The material temperature must be lower than 25°C. It is recommended to paint the surface with Color Prime S or Color Prime Plus before the finish application. Surfaces must be lightly sanded before application of primer.

Dryvit Reinforced Base Coat: The base coat must be dry and cured for a minimum of 24 hours before application of primer and finish.

Concrete: Shall have cured a minimum of 28 days prior to application of the finishes. If efflorescence, form release agents or curing compounds are present on the concrete surface, the surface shall be thoroughly washed with Dryvit Efflorescence Remover or equivalent product and flushed to remove residual acid. All projections shall be removed and small voids filled with Dryvit Fibercoat or Genesis DM Plus (see product data sheets for mixing and application) prior to the application of PMR finishes.

Masonry: The masonry surface, with joints struck flush, shall be "skim coated" with Dryvit Fibercoat or Genesis DM Plus (see product data sheets for mixing and application) to produce a smooth, level surface.

Render: Primer and finish shall be applied over the cured base coat. If additives are present in the stucco, a test patch shall be made and bond strength checked prior to application.

MIXING

Mix PMR finishes with a slow speed drill (400-500 rpm) for approximately 1-1.5 minutes and paddle until a uniform workable consistency is attained, just prior to application. A small amount of clean potable water may be added to adjust workability. Always add the same amount of water to each pail to avoid colour variation.

APPLICATION METHOD

Using a stainless steel trowel, apply and level a coat of PMR finish to a uniform thickness (no thicker than the largest aggregate size). Float the finish lightly with a plastic float. Use the same final trowelling tool and hand motion over the entire wall. Texture of Freestyle finish can be shaped freely but the thickness of the finish texture shall not exceed 3.0 mm. The application of the finish should be done constantly (without interruptions).

MAINTENANCE

PMR finishes can be washed using suitable fungicidal wash. After application the washed surface should be rinsed with water. Maximum cleaning pressure of 120 atmospheres. The distance of the washing nozzle from the wall should be 0.4-0.5 m.

Information contained in this product data sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit UK Ltd. products as of the date of publication of this document and is presented in good faith. Dryvit UK Ltd. assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit UK Ltd.

Manufacturing locations: Dryvit Systems USA (Europe) Krze Duze7; 96-325 Radziejowice, Poland, BDO: 000104176

STORAGE

Store in sealed original packaging, in dry condition at temperatures between 4°C and 38°C, for a maximum of 24 months from the production date indicated on the packaging. Protect the packaging against damages and direct impact of atmospheric conditions and moisture.

CAUTIONS & LIMITATIONS

PMR finishes must not be used on exposed exterior horizontal surfaces. Minimum slope is 6 in 12 which is 27°. Maximum length of slope is 300 mm. PMR finishes shall not be used below grade.

PMR finishes are not intended for direct-applied, vertical applications over exterior type gypsum based sheathing board, foam plastic insulation or other type insulation board.

PMR finishes shall not be returned into any sealant joint. Instead, a coat of Dryvit Color Prime, Color Prime Plus or Dryvit Demandit Smooth should be applied over the base coat in the joint.

Minimise exposure of materials to temperatures over 38°C. PMR finishes exposed to temperatures above this for even short periods may exhibit skinning, increased viscosity, and should be inspected prior to use.

CLEANING

All equipment must be washed with clean water immediately after use and while the finishes are still wet. Disposal must be in accordance with local and national legislation and must not be emptied into drainage systems.

HEALTH & SAFETY

For information on handling the product, storage and disposal refer to the current safety data sheet (SDS) available at www.dryvit.co.uk

FURTHER INFORMATION Refer to the relevant System Application Instructions and the product Safety Data Sheet.

APPROVALS:

ETA - 18/0944 Dryvit Roxsulation Pro System

Dryvit UK Ltd
Unit 4 Wren Park
Hitchin Road
Shefford
Bedfordshire
SG17 5JD
01462 819555
Email: ukenquiries@dryvit.com
www.dryvit.co.uk

